



WTVE0429LU
CLEAR 2K GLOSSY WATERBORNE TOPCOAT 429

Descriptive notes Clear waterborne glossy 2 pack topcoat, for spray applications. Compatible with water-based pastes ICROMIX 2.0.

Gloss Versions	Glossy							
-----------------------	--------	--	--	--	--	--	--	--

USAGE

Suitable for	Furniture	Turned wood					
Method of application	Spray	Air mixing spray painting					

MAIN PROPERTIES

Filling	High	Easy Application	High
Transparency	High	Yellowing Resistance	High
Drying	Slow	Scratch Resistance	High

PREPARATION OF THE PRODUCT

	Code	%	Descriptive notes
Recommended thinner	Water	0 ÷5	Add after mixing of the hardener
Other thinners			
Recommended hardener	INUR0982	30	Mix with a low / medium speed mechanical stirrer
Other hardeners			
Accelerant.			

CHEMICAL-PHYSICAL CHARACTERISTICS		APPLICATION CHARACTERISTICS		DRYING	
Specific gravity (kg/l) ±0.03	1,03	N° of coats	1	Dust free (min)	40÷50
Solids Content (%) ±1	35	Qty. per coat (g/m²)	100÷130	Touch dry (min)	180÷240
Viscosity DIN 4 (20°C)	40"÷50"				

Additional information: The product is formulated only in opacity shown above. It's recommended to dry with oven at 30°-40°C, after the dust free time.

Store the product in room where the temperature does not fall below 5°C. If properly stored, the shelf-life is 12 months. During application, keep the product and the substrate at a temperature of at least 15°C. The use of coating devices not in perfect order may cause major defects in the coating film.

WARNING Our data sheets are drawn up on the basis of average results of our trials. However our tech tips are given in good faith but without guarantee. In fact, several media, conditions of application, plant and dilutions are an integral part of the final result and often beyond our control. The user must try the products supplied to test whether suitable to your needs. For our part we guarantee the continuity of the chemical-physical characteristics.

Warning: it is the user's responsibility to provide that the application is in properly ventilated environment hygienic and in accordance with standards and accident prevention regulations currently in force.

Revision n° 2	Revision Date: 02/02/24	Printed: 02/02/2024
---------------	-------------------------	---------------------