



WTVE0754
ICRONATURAL

Descriptive notes

Waterborne 1-pack or 2-pack topcoat with natural wood effect: keeps the natural beauty of the wood.



As 1-pack is ready to use. If used as 2-pack, add under stirring 10% of hardener INUR0350. Applied to the brush should be diluted to 10% with water.

Gloss Versions	0							
-----------------------	---	--	--	--	--	--	--	--

USAGE

Suitable for	Parquet	Cabinet doors	Furniture	Panelling	Internal doors and shutters	Frames	
Method of application	Hand roller	Brush	Spray				

MAIN PROPERTIES

Filling	For open pores	Easy Application	High
Transparency	High	Yellowing Resistance	High
Fast drying	Medium/ fast	Scratch Resistance	High

PREPARATION OF THE PRODUCT

	Code	%	Descriptive notes
Recommended thinner	Acqua	5→15	
Other thinners			
Recommended hardener	INUR0350	0→10	
Other hardeners			
Accelerant.			

CHEMICAL-PHYSICAL CHARACTERISTICS		APPLICATION CHARACTERISTICS		DRYING	
Specific gravity (kg/l) ±0.03	1,01	N° of hands	1+2	Dust free (min)	20÷40
Solids Content (%) ±1	30	Qty. per coat (g/m²)	100÷120	Touch dry (min)	90÷120
Viscosity DIN 4 (20°C) 4	38"÷42"	Interval between coats (h)	3÷4		
		Yield (m²/l)	10÷12	Stackable (h)	24÷48
				Sanded (h)	4÷6

Additional information:

► For parquet: after filled and sanded the floor (final sanding with 180 grit paper), clean the surface and apply two coats of WTVE0754 approximately 120 g/m² for coat, interval between 2 + 4 hour for coat with light sanding in between. ► It must be applied at a temperature not lower than 10°C. ► Equipment cleaning: use water or soapy water. Note: clean immediately after use. ► If properly stored at a temperature between 5°C + 35°C shelf life is 12 months.

WARNING

Our data sheets are drawn up on the basis of average results of our trials. However our tech tips are given in good faith but without guarantee. In fact, several media, conditions of application, plant and dilutions are an integral part of the final result and often beyond our control. The user must try the products supplied to test whether suitable to your needs. For our part we guarantee the continuity of the chemical-physical characteristics.
Warning: it is the user's responsibility to provide that the application is in properly ventilated environment hygienic and in accordance with standards and accident prevention regulations currently in force.

Revision n° 7	Revision Date 14/02/2019
---------------	--------------------------

Printed:	14/02/2019
----------	------------